

MILASTIC[®] 15

TEXTURED ELASTOMERIC COATING 551211

Textured Elastomeric Masonry Coating

Milastic 15 is a premium quality 100% acrylic, internally plasticized acrylic emulsion elastomeric coating for exterior concrete, stucco, and various concrete block substrates. Ideal for tilt-up buildings on properly cured concrete, Milastic 15 expands and contracts with the substrate thereby resisting surface cracking. It will bridge and seal small hairline cracks and minor surface imperfections. The high build requires several days for thorough cure.

	PRODUCT
Resin:	Acrylic
Color Range:	White and Deeptone Tints
Finish:	0-6 @ 60°
	0-10 @ 85° Gloss Level 1
Drying Time:	To Touch: 4 Hours
(70° F & 50% R.H.)	To Recoat: 24 Hours
Clean Up:	Soap & Water
Sizes:	Gallons, Fives
•	·

Tint Bases: Textured White 551211

Texture: 30 Mesh

Weight Per Gallon:	11.4
Solids by Weight:	62% ± 2%
Solids by Volume:	54% ± 2%
Recommended Film	Wet: 12 - 14 mils per coat
Thickness:	Dry: 12 - 15 mils pinhole free (2 coats)
Practical Coverage:	250 - 400 FT ² Per Gallon
Smooth Surfaces	100 - 130 FT ² Per Gallon
Textured Surfaces	50 - 100 FT ² Per Gallon
Two Coats Minimum @ 120 FT ² Per Gallon over sealed surface	

<50 g/L*

Greenseal GS-11 Standard

*Maximum VOC content for non-tinted paint base is less than 50 g/L (40 CFR 59.406). VOC content may increase

REGULATORY COMPLIANCE

Architectural and Industrial Maintenence Coating (AIM - EPA) South Coast Air Quality Management District (SCAQMD) California Air Resources Board (CARB)

SURFACE PREPARATION

General: All surfaces must be firm, dry and cleaned free of loose paint, dust, dirt, oil, grease, wax, chalk, rust, mildew or any other contamination or condition that would adversely affect the performance of the coating. De-gloss shiny surfaces by lightly sanding†. Repair cracks and fill voids.

†See warning for existing lead-based paint under Precautions.

New Surfaces:

Follow general surface preparation guidelines. New concrete or stucco must cure for 30 days prior to coating. Moisture content should be less than 12 % as measured with a moisture meter and the pH should be between 7 and 11. Remove all laitance and efflorescence before priming with the appropriate primer.

Previously Painted Surfaces:

Follow general surface preparation guidelines. Remove loose or failing paint and spot prime bare areas or entire surface with the appropriate primer. Hard, glossy surfaces may require sanding and/or a bonding primer. Spraying and Backrolling recommended on new flat work. To avoid lap marks, maintain a wet edge. Keep product from freezing.

APPLICATION

Brush: **Nylon/Polyester Brush Roller:** 3/4" - 1" Nap Synthetic Cover .019" - .030" Tip Size Airless Spray:

RECOMMENDED PRIMERS

Concrete, Ph Surfacer Int/Ext Alkali Resistant Primer 620011 Stucco, and Masonry: Concrete Block: Block Filler 481011

Wood: All Purpose Int/Ext Stain Blocking Primer 470011 Ferrous Metal, Acrimetal DTM Low Sheen Primer/Finish 310210 Galvanized Metal, or All Purpose Int/Ext Stain Blocking Primer 470011 Aluminum:

Gypsum Wallboard: All Purpose Int/Ext Stain Blocking Primer 470011 Ph Surfacer Int/Ext Alkali Resistant Primer 620011

OTHER PRIMERS MAY BE APPROPRIATE. CONTACT MILLER PAINT FOR MORE INFORMATION.

TESTING INFORMATION

ASTM D 522 Flexibility: @ -30°F: Passed @ 75°F: 749% **ASTM D 412 Elongation:** @ 0°F: 331%

Wind Driven Rain Resistance: Passed (Fed Spec. TT-C-555B, par. 4.4.7)

THINNING

Apply at can consistency. If thinning is necessary to maintain workability, do not exceed one-half pint of water per gallon. Stir product thoroughly.

Surface and air temperatures should be between 35°F and 95°F during application and for 48 hours after application. Humidity should be below 80%. Surface temperature should be at least 5°F above dew point. Do not paint if temperatures are expected to drop below 35°F. Do not paint late in the day when excessive dew, condensation, rain, or snow is expected. Large metal surfaces should be painted in temperatures above 50°F.

PRECAUTIONS

WARNING! If you scrape, sand, or remove old paint from any surface, you may release lead dust, LEAD IS TOXIC, EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAM-AGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

Avoid contact with eyes, skin and clothing. Do not take internally. Wash thoroughly after handling. Close container after each use. For additional safety information, consult the Material Safety Data Sheet for this product.

USE ONLY WITH ADEQUATE VENTILATION

KEEP OUT OF REACH OF CHILDREN

Miller Paint warrants satisfactory results of our products if used according to label directions. If not satisfied, return the unused portion to place of purchase with a sales receipt. Material will be replaced or purchase price will be refunded. Since we have no control over surface preparation or application, THIS WARRANTY DOES NOT INCLUDE LABOR, THE COST OF LABOR OR INCIDENTAL OR CONSEQUENTIAL DAMAGES ASSOCIATED WITH USE OF THIS PRODUCT. Some states do not allow the exclusion of incidental or consequential damages, so the limitation or exclusion contained in the above warranty may not apply to you. This warranty gives you specific legal rights. You may also have other rights which vary from state to state.

Never pour leftover coating down any sink or drain – use up material on the job or seal can and store safely for future use. Do not incinerate closed containers. For specific disposal or recycle guidelines, contact your local waste management agency or district. Please re-use or recycle.